



**CG 2WA Grout for Tiles**

<b>PRODUCT NAME</b>	<b>MATHIOS GROUT</b>
<b>General Information (EN 13888):</b>	Improved cementitious grout, with additional characteristics of reduced water absorption and high abrasion resistance
<b>Water Mixing Ratio:</b>	10-13%
<b>Application Temperature:</b>	From +5 °C up to + 35 °C
<b>Workability:</b>	≥ 120 min
<b>Setting Time:</b>	30 min
<b>FINAL PROPERTIES</b>	
<b>Abrasion Resistance (EN 12808-2)</b>	≥ 900 mm <sup>3</sup>
<b>Mechanical Strength (EN 1208-3)</b>	≥ 17 N/ mm <sup>2</sup>
<b>Shrinkage (EN 1208-4)</b>	≤ 0,66 mm/m
<b>Water Absorption (EN 1208-5)</b>	After 30 min: 1,21g After 120 min: 2,21g
<b>Allowed Temperature Applications:</b>	+ 5 °C up to + 35 °C
<b>Categorization (EN 13888)</b>	CG 2WA
<b>Consumption:</b>	From 5 – 14 kg/m <sup>2</sup> provisional the grout size and the type of stone or brick
<b>Storage Conditions:</b>	Can be stored dry in its original sealed packing for 12 months

The above data are typical average values obtained in accordance with the accepted harmonized EN test methods and are subject to normal manufacturing variations. They may not be regarded as binding specifications. All previously published product-information are replaced by the values stated here and thus become invalid.